

AQUACER 1063

Polyethylene primary dispersion to improve the anti-caking properties of hot-melt adhesives and to increase adhesion in dispersion adhesives for the packaging sector.

Product Data

Composition

Polyethylene primary dispersion with anionic and non-ionic emulsifying agents

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Non-volatile matter (60 min., 125 °C):	40 %
Carrier:	Water
Melting point (wax content):	95 °C
Viscosity (20 °C):	< 250 mPa·s
pH value (20 °C):	9

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Temperature sensitive. To be stored and transported between 5 °C and 35 °C. Mix well before use.

Applications

Hot-melt adhesives

Special Features and Benefits

AQUACER 1063 is used as an anti-blocking additive in the manufacture of hot-melt adhesives (hot-melts) during underwater pelletizing to obtain a free-flowing, non-sticky granulate. It is added directly into the cooling water and is therefore easy to handle and dust-free.

Recommended Levels

0.5-5 % additive (as supplied) based on the quantity of water in the cooling system.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive is added directly into the circulation water. If foam builds up in the circulation water, we recommend using a defoamer, for example BYK-1679 (silicone defoamer) or BYK-016 (silicone-free) at a dose of 0.05-0.3 %.

Packaging adhesives

Special Features and Benefits

AQUACER 1063 improves adhesion in aqueous dispersion adhesives for the packaging sector. When bonding foil-laminated surfaces with paper or cardboard, AQUACER 1063 improves the adhesion of the laminated side. Adhesion is particularly improved on foils made from oriented polypropylene (OPP), biaxially oriented PP (BOPP), and improved to some extent on polyethylene (PE). The product exhibits good adhesion even at low temperatures. AQUACER 1063 shows no discoloration when bonding systems are stored at higher temperatures.

Recommended Levels

10-50 % additive (as supplied) based on the total formulation.

AQUACER 1063 represents part of the binder in this application which explains the higher levels used. The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive should be added after the binder has been added. Mix well before use.



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYPK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany