

# BYK-067 A

Silicone defoamer for solvent-free and solvent-borne printing inks and overprint varnishes as well as adhesives, sealants, and ambient curing plastic systems. Solvent-free version of BYK-066 N. Odorless.

## Product Data

### Composition

Non-aqueous emulsion of a foam-destroying polysiloxane

### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C):	1.08 g/ml
Non-volatile matter (20 min., 150 °C):	89 %
Carrier:	Propylene glycol
Flash point:	> 100 °C

### Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit [www.byk.com](http://www.byk.com) for further information.

### Storage and Transportation

Separation or turbidity may occur at temperatures below 5 °C. Warm to 20 °C and mix well.

### Special Note

The additive contains fluoro-modified silicone.

## Applications

### Printing inks and overprint varnishes

#### Special Features and Benefits

BYK-067 A is a defoamer for all solvent-borne and solvent-free printing inks and overprint varnishes. This additive is the solvent-free and odor-free version of BYK-066 N and is particularly suitable for aromatic-free systems.

#### Recommended Use

Solvent-borne and solvent-free printing inks and overprint varnishes.

#### Recommended Levels

0.1-0.7 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

**Incorporation and Processing Instructions**

To achieve optimal defoaming, the defoamer should be added to the millbase. If it is incorporated at a later time, sufficient shear forces must be ensured in order to achieve good defoamer distribution and to prevent crater formation.

**Adhesives & Sealants****Special Features and Benefits**

BYK-067 A is a defoamer for all solvent-borne and solvent-free adhesives and sealants (filled and unfilled). It is especially recommended for polyurethane-based systems and is particularly effective in thick layer applications.

**Recommended Levels**

0.1-1 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

**Incorporation and Processing Instructions**

Incorporate into resin before adding the other components.

**Ambient Curing Systems****Special Features and Benefits**

Air release agent to prevent foam and bubbles during the manufacture and application of ambient curing plastic applications.

**Recommended Use**

Recommended for flooring on polyurethane basis.

**Recommended Levels**

0.1-1.5 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

**Incorporation and Processing Instructions**

Incorporate into resin before adding the other components. Can also be added to complete systems.