

BYK-A 555

Silicone-free polymer-based air release additive for unsaturated polyester resins. Suitable for all types of unsaturated polyester resins and processing methods. In particular, also suitable for pultrusion applications with acrylic, unsaturated polyester and vinyl ester resins.

Product Data

Composition

Solution of foam-destroying polymers, silicone-free

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C):	0.88 g/ml
Refractive index (20 °C):	1.507
Flash point:	43 °C
Hazen color number:	< 250
Turbidity:	< 10 TE/F

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Applications

Ambient Curing Systems

Special Features and Benefits

BYK-A 555 displays the highest efficiency in deaerating virtually all unsaturated polyester resins in all processing methods. Air release additive may cause haze in the finished part in some resins.

Recommended Levels

0.1-0.5 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

Stir into the resin before adding other components.

Pultrusion**Special Features and Benefits**

Prevention of air entrapment during the manufacture and application (pultrusion) of plastic systems.

Recommended Use

Recommended for systems based on acrylates, unsaturated polyesters or vinyl ester resins.

Recommended Levels

0.2 phr additive (as supplied) in combination with 0.3 phr BYK-A 515 or BYK-A 560.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

Stir into the resin before adding other components.



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYPK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, PRIEX®, PURE THIX®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany