

BYK-LP R 7095

Viscosity Depressant for PVC Plastisols

Composition

BYK-LP R 7095	Aliphatic hydrocarbons with neutral wetting and dispersing component
----------------------	--

Typical Properties

	Density at 20°C in g/ml	Flash point in °C	Refractive index at 20°C	Appearance
BYK-LP R 7095	0,83	105	1,454	colorless, liquid

Values indicated in this data sheet describe typical properties and do not constitute specification limits.

Recommended Levels

	% additive (as supplied) based upon PVC resin
BYK-LP R 7095	1,0 - 7,5

Incorporation and Processing Instructions

The additive can be added during the production of the plastisol or shortly before processing.

Applications

	PVC Plastisols			
	highly filled	low/unfilled	foamed	pigmented
BYK-LP R 7095	■	■	■	■

■ recommended

BYK-Chemie GmbH
P.O. Box 100245
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKOPLAST®, BYKUMEN®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYPK®, SILBYK® and VISCOBYK® are registered trademarks of BYK-Chemie.
AQUACER®, AQUAFLOUR®, AQUAMAT®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX® and MINERPOL® are registered trademarks of BYK-Cera.

This information is given to the best of our knowledge. Because of the multitude of formulations, production and application conditions, all the above mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This data sheet replaces all previous issues - Printed in Germany