

BYK-W 9010

Wetting and dispersing additive for filled, unsaturated polyester systems and epoxy systems.

Product Data

Composition

Copolymer with acidic groups

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Acid value: 129 mg KOH/g
Density (20 °C): 1.16 g/ml
Refractive index (20 °C): 1.469
Water content: 0.02 %
Active substance: 100 %

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Separation or turbidity may occur. Mix well before use. Warm to 30-40 °C and mix well.

Applications

SMC, BMC, Pultrusion

Special Features and Benefits

Solvent-free wetting and dispersing additive (100 % active substance) to wet inorganic fillers (and inorganic pigments) in systems in which solvents need to be avoided.

Recommended Use

Low emission SMC/BMC	■
LP and Class A formulations	■
LS formulations	■
Epoxy systems	□
Pultrusion	■
Viscosity stabilization BMC	■

■ especially recommended □ recommended

Recommended Levels

0.5-1 % additive (as supplied) based upon fillers for wetting and dispersion.

0.25-1 % additive (as supplied) based upon resin for stabilizing the viscosity in BMC.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

BYK-W 9010 should be added to the resin mixture prior to homogenization and the addition of the fillers/pigments.

Adhesives & Sealants**Special Features and Benefits**

Solvent-free wetting and dispersing additive (100 % active substance) to wet inorganic fillers (and inorganic pigments) in systems in which solvents need to be avoided.

Recommended Use

The additive is particularly recommended for adhesives based on epoxy resins and UV systems.

Recommended Levels

0.5-1 % additive (as supplied) based on the filler.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

For optimum performance, the additive should be added before the solids.



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYPK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany