

BYK-W 969

Wetting and dispersing additive for amine-accelerated UP, EP and, PUR systems and adhesives to reduce the viscosity in mineral-filled systems. It is incorporated into the polymer matrix due to its OH functionality. Not suitable for cobalt-accelerated UP resins.

Product Data

Composition

Solution of a hydroxy-functional alkylammonium salt of an acidic copolymer

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Amine value:	30 mg KOH/g
Acid value:	30 mg KOH/g
Density (20 °C):	1.09 g/ml
Refractive index (20 °C):	1.455
Active substance:	40 %
Flash point:	> 100 °C
OH value:	ca. 265 mg KOH/g

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Separation or turbidity may occur during storage and transportation. Warm to 40-60 °C and mix well. Product efficiency is not influenced.

Applications

Ambient Curing Systems

Special Features and Benefits

BYK-W 969 is a monofunctional, deflocculating wetting and dispersing additive for mineral-filled, amine-preaccelerated polyester putty compounds as well as epoxy, acrylic, and polyurethane resins. It improves the wetting and dispersing speed of fillers during dispersion and reduces viscosity to enable an increased filler content to be achieved. The higher filler content improves sandability in applied and cured polyester putty compounds. The additive leads to a considerably increase in gelling time in cobalt-accelerated unsaturated polyester resins. It is suitable for all filled PUR systems. Due to its OH functionality, BYK-W 969 is incorporated in the polymer matrix and is therefore suitable for PUR systems in which fogging and emissions are critical (e.g., automotive applications).

Recommended Levels

Amount of additive (as supplied) based upon the filler:

UP putty compounds:	0.5-1.5 %
PUR systems:	0.5-2 %
Epoxy systems:	0.5-2 %
Acrylate systems:	0.5-2 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

For optimum performance, the additive should be added before the solids.

Adhesives & Sealants**Special Features and Benefits**

BYK-W 969 is a monofunctional, deflocculating wetting and dispersing additive. It is particularly recommended for all filled PUR systems. Due to its OH functionality, this additive is incorporated into the polymer matrix and is therefore suitable for systems in which fogging and emissions are critical (e.g. automotive applications). BYK-W 969 is a wetting and dispersing additive for mineral-filled polyurethane and epoxy adhesives. It improves the wetting and dispersing speed of fillers during dispersion and reduces the viscosity to enable an increased filler content to be achieved.

Recommended Levels

0.5-1 % additive (as supplied) based upon the filler.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

For optimum performance, the additive should be added before the solids.



Additive Guide

**BYK-Chemie GmbH**

P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYPK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany