

BYKO2BLOCK-1200

Barrier additive to reduce gas permeability in packaging films

Product Data

Composition

Modified aluminum-magnesium clay

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Moisture: < 3 %
Typical Dry Particle Size: < 50 µm (d50)
Color: Off white
Packed Bulk Density: 575 g/l

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Store dry.

Applications

Thermoplastics

Recommended Use

BYKO2BLOCK-1200 can be used in films based on biopolymers such as PLA, but it can be also used for other polymers which are used for films, e.g. in the packaging industry.

Polymers, such as PLA (Polylactide) are used more and more as a substitute for conventional polymers like Polypropylene or Polyethylene in the packaging industry due to their green footprint. A significant area of improvement when using PLA for packaging films is the considerably greater permeability for gases such as O₂ and water vapor. BYKO2BLOCK-1200 was developed to reduce the gas permeability of these polymers. The platelet-shaped particles formed during the compounding create a so-called winding pathway for the gases, thereby reducing this the permeability.

Recommended Levels

3-5 % as supplied based on the total formulation

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

To make use of the full performance of BYKO2BLOCK-1200, a complete exfoliation of the clay particles is necessary. To realize this, special care should be taken during the compounding. The use of concurrent, parallel screw extruders, co-rotating-twin-screw-extruders ($L/D > 40$) or buss kneaders is highly recommended to ensure a perfect exfoliation and distribution of the clay particles. In some cases, it is recommended to prepare concentrates of BYKO2BLOCK-1200 up to 15-20 % so as to ensure a good exfoliation of the platelet-shaped filler.

Special Note

For further support regarding processing conditions please contact Jochen.Wilms@altana.com.



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SCONA®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAC®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany