

CARBOBYK-9810

Highly filled, aqueous dispersion of carbon nanotubes to improve the mechanical properties, electrical conductivity, and anti-static behavior.

Product Data

Composition

Dispersion of multiple-wall carbon nanotubes in water

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Carbon nanotubes content:	8 %
Density (20 °C):	1.08 g/ml
Non-volatile matter (20 min., 150 °C):	21 %
Carrier:	Water
Flash point:	> 100 °C

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Temperature for transport and storage must be below 35 °C. Mix well before use.

CARBOBYK-9810 has a pronounced structural viscous behavior. The viscosity increases considerably during storage so that the product becomes a paste. Mixing the product well, e.g. with a dissolver, can reduce the viscosity again to a range of around 100 mPa·s.

Applications

Special Features and Benefits

Incorporating carbon nanotubes in coatings, printing inks, plastics or adhesives will improve the electrical and thermal conductivity, the anti-static behavior, the mechanical properties, and the shielding against electromagnetic waves. The additive is recommended only for aqueous systems.

Recommended Use

Architectural coatings	<input checked="" type="checkbox"/>
Industrial coatings	<input checked="" type="checkbox"/>
Adhesives	<input type="checkbox"/>
Automotive coatings	<input type="checkbox"/>
Plastics industry	<input type="checkbox"/>
Printing inks	<input type="checkbox"/>
Wood coatings	<input type="checkbox"/>

☒ especially recommended ☐ recommended

Recommended Levels

0.3-3 % additive on solids in the formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive should preferably be post-added to the coating using a low shear rate.



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SCONA®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAC®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany