

CERAFAK 127 N

Dispersion of a Fischer Tropsch wax for solvent-borne coil coatings and architectural coatings to improve surface characteristics.

Product Data

Composition

Fischer-Tropsch wax dispersion

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Non-volatile matter:	15 %
Carrier:	Naphthalene-depleted, aromatic hydrocarbons
Melting point (wax content):	120 °C
Particle size distribution (laser diffraction, volume distribution):	D50: 3 µm D90: 7 µm
Viscosity (23 °C, D=200/s):	60 mPa·s

Food Contact Legal Status

The additive is suitable for applications that come into contact with food. For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Temperature sensitive. To be stored and transported at a temperature below 35 °C. Mix well before use.

Applications

Coatings Industry

Special Features and Benefits

The additive increases surface slip and also improves the scratch resistance, it displays good anti-blocking properties and has a hydrophobic effect. It is recommended for solvent-borne coil coatings and architectural coatings.

Recommended Levels

1-5 % additive (as supplied) based on the total formulation in coil coatings.

3-13 % additive (as supplied) based on the total formulation in architectural coatings.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive should preferably be post-added to the coating using a low shear rate. Mix well before use.

CERAFAK 127 N

Data Sheet
Issue 11/2014



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYPK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany