

# CERAFLOUR 981

Micronized PTFE for solvent-borne and solvent-free coating systems and powder coatings to improve the scratch resistance and surface slip.

## Product Data

### Composition

Micronized PTFE

### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density:	2.28 g/ml	
Particle size distribution (laser diffraction, volume distribution):	D50: 3 µm	D90: 6 µm
Supplied as:	Micropowder	

### Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit [www.byk.com](http://www.byk.com) for further information.

### Storage and Transportation

Temperature sensitive. To be stored and transported at a temperature below 50 °C.

## Applications

### Powder Coatings

#### Special Features and Benefits

The additive increases surface slip, scratch resistance and heat resistance of the surfaces.

#### Recommended Use

CERAFLOUR 981 is recommended for powder coatings based on polyester/TGIC/primid/powder link, polyester/epoxide, acrylate, polyurethane and epoxides.

#### Recommended Levels

0.1-0.3 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

#### Incorporation and Processing Instructions

CERAFLOUR 981 should be mixed with the resin, hardener, pigments and other additives using a high-speed mixer and extruded along with all components.

## Liquid Coatings

### Special Features and Benefits

The additive increases the scratch resistance and is suitable for solvent-borne and solvent-free coating systems.

### Recommended Levels

0.1-0.3 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

### Incorporation and Processing Instructions

The additive is preferably incorporated into the coating at the end of the production process at a moderate shear rate.



Additive Guide



**BYK-Chemie GmbH**  
P.O. Box 10 02 45  
46462 Wesel  
Germany  
Tel +49 281 670-0  
Fax +49 281 65735

**info@byk.com**  
**www.byk.com**

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany