

# CERAFLOUR 994

Micronized additive based on an amide wax for solvent-borne coating systems and powder coatings. To improve scratch resistance and sandability, electrostatic charge of powder coatings and meat release properties in can coatings.

## Product Data

### Composition

Ultra-fine micronized amide wax

### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C):	0.99 g/ml	
Melting point:	145 °C	
Particle size distribution (laser diffraction, volume distribution):	D50: 5 µm	D90: 10 µm
Supplied as:	Micropowder	

### Food Contact Legal Status

This additive is suitable for applications with food contact. For the current food contact legal status, please contact our product safety department or visit [www.byk.com](http://www.byk.com) for further information.

### Storage and Transportation

Temperature sensitive. To be stored and transported at a temperature below 50 °C.

## Applications

### Powder Coatings

#### Special Features and Benefits

The additive improves the pigment wetting in the manufacture of powder coatings and the electrostatic charge during application.

#### Recommended Use

CERAFLOUR 994 is recommended for powder coatings based on polyester, polyester/epoxide, acrylate, polyurethane and epoxides.

#### Recommended Levels

0.5-2 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

#### Incorporation and Processing Instructions

CERAFLOUR 994 should be mixed with resin, hardener, pigments and other additives using a high-speed mixer and extruded along with all components.

### Liquid Coatings

#### Special Features and Benefits

The additive improves scratch resistance and sandability and reduces the gloss in all solvent-borne and solvent-free coating systems. Meat release properties in can coatings are improved.

#### Recommended Levels

0.5-2 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

#### Incorporation and Processing Instructions

The additive is preferably incorporated into the coating at the end of the production process at a moderate shear rate.



Additive Guide



**BYK-Chemie GmbH**  
P.O. Box 10 02 45

46462 Wesel  
Germany  
Tel +49 281 670-0  
Fax +49 281 65735

[info@byk.com](mailto:info@byk.com)  
[www.byk.com/additives](http://www.byk.com/additives)

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This issue replaces all previous versions – Printed in Germany