Data Sheet Issue 12/2013

# **CERATIX 8466**

Aromatic-free wax dispersion based on an EVA copolymer for solvent-borne effect coating systems to improve the orientation of effect pigments. It reduces settling of the effect pigments in the circulation pipe and in the container.

# **Product Data**

Composition Aromatic-free

Ethylene vinyl acetate copolymer wax dispersion (EVA)

# **Typical Properties**

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Non-volatile matter (1 h, 125 °C): 4.7 %

Solvents: Butylacetate/n-butanol 9/1

Flash point: 27 °C Melting point (wax content): 100 °C Viscosity (23 °C): 16 mPa·s

# **Food Contact Legal Status**

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

# **Storage and Transportation**

Temperature sensitive. To be stored and transported at a temperature below 35 °C. Mix well before use.

## **Special Note**

### Test method: Seeding

The wax additive is homogenized with a dissolver for 5 min at 4 m/s, then diluted with 20 % n-butylacetate and stirred for a further 2 min at about 4 m/s. A draw down is then made on a glass panel with a 100  $\mu$ m doctor blade. The result must be clear during the drying and free from seeds.

Test method: Particle size measurement with a grindometer according to ISO 1524

The wax additive is homogenized with a dissolver for 5 min at 4 m/s. A draw down is then made on a 50  $\mu$ m grindometer. Result: 20  $\mu$ m fineness of grind.

# **Applications**

# **Coatings Industry**

# **Special Features and Benefits**

The aromatic-free additive improves the orientation of effect pigments (aluminum, mica etc.), reduces large scale clouding and minimizes short wave defects (mottling, Bénard cells). It enhances the flip-flop effect and improves the leveling of the subsequent clear coating. Due to the special rheological properties of CERATIX 8466, it also reduces the settling of the effect pigments in the container and in the circulation pipe.

Data Sheet Issue 12/2013

#### **Recommended Use**

The additive is recommended for all solvent-borne base coats and one coat top coats with effect pigments.

Automotive coatings	
Industrial coatings	

especially recommended


## **Recommended Levels**

40-70 % additive (as supplied) based upon solid binder.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

# **Incorporation and Processing Instructions**

The wax additive must be homogenized before use with a dissolver (4 m/s) and then added to the binder solution under agitation. In systems with CAB, the CAB solution must first be incorporated homogeneously in the binder solution at high shear forces (> 5 m/s) before the stirred wax additive, the effect pigment slurry and the solvents can be added under agitation.



# **Special Note**

CERATIX 8461 and CERATIX 8463 are two other wax additives which are very similar to CERATIX 8466. CERATIX 8463 is more polar than the other two and CERATIX 8466 is aromatic-free. Choosing the most suitable CERATIX type depends on the polarity of the base coat and of the clear coat. The choice can be determined by carrying out comparative testing.







Fax +49 281 65735 info@byk.com www.byk.com/additives ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERBYK®, DISPERBYKB, ANTI-CERAFICAL, BYKLOFTA, BYKLOFTA, BYKLOFTA, BYKLOFTA, DISPERBYKB, DISPERB

SCONA® is a registered trademark of BYK Kometra.

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This issue replaces all previous versions – Printed in Germany