

CLAYTONE HY

Rheological Additive

Product Data

Special Features and Benefits

CLAYTONE HY is a modified montmorillonite designed to be used in aliphatic, aromatic and polar systems that exhibit almost any polarity. CLAYTONE HY can be used to replace multiple grades of other organoclays and may function as a universal organoclay. CLAYTONE HY functions as a thixotropic rheology modifier generating properties such as flow control, anti-misting and anti-setting. CLAYTONE HY provides reliable and reproducible rheological properties in solvent based paints, stains, enamels, primers, and inks as well as other applications. CLAYTONE HY does not require the use of a polar activator to achieve full efficiency.

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Color:	Very light cream
Form:	Free flowing, finely divided powder
Moisture:	<2.0 %
Loss on Ignition (1000 °C/1800 °F):	41.5-44.5
Specific Gravity (Density):	Metric 1.6 g/cm ³ , English 13.3 lbs./gal.
Bulk Density:	Metric 240 - 340 g/l, English 15 - 21 lbs/ft. ³
Dry Sieve Size:	Metric 98 % <32µm, English 98 % <450 mesh

Recommended Use

- Oil based paints and stains
- Adhesives
- Caulks and sealants
- Cosmetics and personal care
- Inks

Incorporation and Processing Instructions

CLAYTONE HY does not require heat for dispersion. It may be incorporated in the grind phase and subjected to high shear. Alternatively, in many formulations CLAYTONE HY can be post added under high shear.

Recommended Levels

Use levels of CLAYTONE HY are typically 0.2 % to 2.0 % of the weight of the system.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Storage and Transportation

Typically CLAYTONE HY can be stored under dry conditions between temperatures of 0 °C and 30 °C (32 °F to 85 °F) for up to two years.

CLAYTONE HY

Data Sheet
Issue 10/2013

BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com/additives

ACTAL®, ADJUST-4®, ADVITROL®, BENTOLITE®, CLAYTONE®, CLOISITE®, COPISIL®, FULACOLOR®, FULCAT®, FULGEL®, FULMONT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PERMONT®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, SCP®, TIXOGEL®, Y25® are registered trademarks of BYK Additives.

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYPK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This issue replaces all previous versions – Printed in Germany