

DISPERBYK-171

Wetting and dispersing additive to produce pigment concentrates for unsaturated polyester resin systems and gel coats.

Product Data

Composition

Solution of a high molecular weight block copolymer with pigment affinic groups

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Non-volatile matter (120 min., 105 °C):	39.5 %
Acid value:	13 mg KOH/g
Density (20 °C):	1.02 g/ml
Solvents:	Methoxypropylacetate/butylacetate 4/1
Flash point:	> 35 °C

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Separation or turbidity may occur at temperatures below 5 °C. Warm to 20 °C and mix well.

Applications

Ambient Curing Resin Systems

Special Features and Benefits

DISPERBYK-171 deflocculates pigments by means of steric stabilization. As a result of the small particle size of the deflocculated pigments, color strength is improved. Moreover, the viscosity is reduced so that a higher pigment loading is possible. DISPERBYK-171 prevents flooding/floating, even in complex pigment/paste combinations and difficult colors.

Recommended Use

Particularly recommended for producing pigment concentrates for gel coats; also recommended to stabilize pigments in gel coats.

Recommended Levels

Amount of additive (as supplied) based upon pigment:

Inorganic pigments: 10-18 %
Titanium dioxides: 4-6 %
Organic pigments: 35-60 %
Carbon blacks: 70-120 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

For optimum performance, DISPERBYK-171 should be added slowly to the resin whilst stirring. Only add the pigments once the additive has been uniformly distributed. Dispersion then takes place and finally, more resin is added if necessary.



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com/additives

ACTAL®, ADJUST®, ADVITROL®, ALUFERSOL®, ANTI-TERRA®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CLAYTONE®, CLOISITE®, COPISIL®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, FULGEL®, FULMONT®, GARAMITE®, GELWHITE®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, SILBYK®, TIXOGEL®, VISCOBYK®, Y-25®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This issue replaces all previous versions – Printed in Germany