

HORDAMER PE 03

Primary polyethylene dispersion for formulating release agents for metal die casting.

Product Data

Composition

Primary polyethylene dispersion with anionic and non-ionic emulsifiers

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

| | |
|------------------------------------|-----------|
| Density (20 °C): | 0.98 g/ml |
| Non-volatile matter (1 h, 125 °C): | 40 % |
| Carrier: | Water |
| Melting point (wax content): | 95 °C |
| Viscosity (20 °C): | 20 mPa·s |
| pH value (20 °C): | 9 |

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Temperature sensitive. To be stored and transported between 5 °C and 35 °C. Mix well before use.

Applications

Release Agents for Metal Die Casting

Special Features and Benefits

HORDAMER PE 03 is recommended for formulating aqueous mold release agents which are used in aluminum die casting. The product brings about a good wetting of the mold at high temperatures, very good film forming and outstanding adhesion to the mold surface. The mold is protected from damage and the finished molded components have an excellent surface quality. HORDAMER PE 03 also remains stable in hard water.

Recommended Levels

10-70 % additive PE 03 (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

HORDAMER PE 03 is preferably diluted with water, but can also be mixed directly with all the components of the aqueous mold release agent.

HORDAMER PE 03

Data Sheet
Issue 05/2014



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany