

# NANOBYK-3610

Nanoparticle dispersion (surface-treated aluminum oxide) to improve the scratch resistance of solvent-borne wood coatings and industrial coatings.

## Product Data

### Composition

Dispersion of surface-treated aluminum oxide nanoparticles

### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C):	1.25 g/ml
Non-volatile matter (10 min., 150 °C):	37 %
Carrier:	Methoxypropylacetate
Flash point:	40 °C
Nanoparticle content:	30 %
Particle size D50:	20 nm
Viscosity (20 °C):	10 mPa·s

### Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit [www.byk.com](http://www.byk.com) for further information.

### Storage and Transportation

To be stored and transported at a temperature below 40 °C. Separation or turbidity may occur during storage and transportation. Mix well before use.

### Special Note

The product must be stirred thoroughly before processing. Dried additive residues must be removed from the container since they can lead to seeding when introduced into the final product.

## Applications

### Coatings Industry

#### Special Features and Benefits

The additive improves the scratch resistance of coating surfaces. Even low levels of 0.5-6.0 % NANOBYK-3610 considerably improve the scratch resistance without having a significant impact on the optical coating properties such as gloss, color, transparency and other physical properties.

## Recommended Levels

0.5-6.0 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

## Incorporation and Processing Instructions

The product reaches its full effectiveness when added at low shear forces. This ensures that even distribution in the binder system is achieved.



Additive Guide



**BYK-Chemie GmbH**  
P.O. Box 10 02 45

46462 Wesel  
Germany  
Tel +49 281 670-0  
Fax +49 281 65735

[info@byk.com](mailto:info@byk.com)  
[www.byk.com/additives](http://www.byk.com/additives)

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This issue replaces all previous versions – Printed in Germany