

# OPTIGEL-WA

Rheology additive based on an activated phyllosilicate for aqueous coating systems and dispersion-based construction applications to generate thixotropic flow behavior.

## Product Data

### Composition

Activated phyllosilicate

### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Specific density: 2.4 g/cm<sup>3</sup>  
Bulk density: 400-600 kg/m<sup>3</sup>  
Moisture content: 9 % ± 3 %  
Supplied as: free-flowing, white powder  
pH value (2 % in H<sub>2</sub>O): 7-8

### Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit [www.byk.com](http://www.byk.com) for further information.

### Storage and Transportation

OPTIGEL-WA is hygroscopic and should be transported and stored dry in the unopened original container at temperatures between 0 °C and 30 °C.

## Applications

### Coatings Industry

#### Special Features and Benefits

OPTIGEL-WA generates thixotropic flow behavior. It improves processability and storage stability as it is highly effective at preventing solids settling. In addition, it reduces the sagging tendency after application which makes it possible to achieve greater layer thicknesses.

#### Recommended Use

OPTIGEL-WA is suitable for a variety of aqueous coating systems. It can be used in pH-neutral and alkaline systems.

Architectural coatings	■
Wood and furniture coatings	■

■ especially recommended    □ recommended

**Recommended Levels**

0.3-2.0 % additive (as supplied) based upon the total formulation, depending on the properties of the formulation to be achieved.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

**Incorporation and Processing Instructions**

OPTIGEL-WA is hydrophilic and easy to incorporate in water. To ensure optimum distribution and the best possible effectiveness and reproducibility in applications, the additive must be added to water (20 °C ± 5 °C) slowly whilst stirring, and pre-dispersed at high shear forces for at least 20 minutes. OPTIGEL-WA should be fully hydrated before the remaining formulation components can be added to the dispersion. No wetting or dispersing additives are required to produce this dispersion.

OPTIGEL-WA can also be added to the formulation directly, as a powder at the start of manufacture (post-added).

**Construction industry****Special Features and Benefits**

In free-flowing systems, OPTIGEL-WA prevents the aggregate settling and the tendency towards syneresis. In high-solid construction systems it achieves smooth processability and improved anti-sagging properties.

**Recommended Use**

OPTIGEL-WA is suitable for emulsion-based plaster or adhesive systems.

Paste-like tile adhesives	<input checked="" type="checkbox"/>
Paste-like putty compounds	<input checked="" type="checkbox"/>

☒ especially recommended    ☐ recommended

**Recommended Levels**

0.2-1 % additive (as supplied) based upon the total formulation, depending on the properties of the formulation to be achieved.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

**Incorporation and Processing Instructions**

OPTIGEL-WA is hydrophilic, we therefore recommend pre-dispersing in water. The additive should be added to water slowly whilst stirring, and pre-dispersed at high shear forces for at least 20 minutes. All other system components can then be added to the dispersion.

## Adhesives and sealants

### Special Features and Benefits

OPTIGEL-WA generates thixotropic flow behavior in adhesives and sealants. It improves processability and storage stability as it is highly effective at preventing solids settling. It improves the slip behavior, anti-sagging properties and ridge formation. OPTIGEL-WA is inorganic and stable to diluted acids and bases.

### Recommended Use

OPTIGEL-WA is suitable for a variety of aqueous systems. It is suitable for pH neutral, acidic and basic adhesives and sealants.

Floor adhesives	<input checked="" type="checkbox"/>
Acrylate sealants	<input checked="" type="checkbox"/>
Wood glues	<input checked="" type="checkbox"/>
Dispersion adhesives	<input checked="" type="checkbox"/>

☒ especially recommended    ☐ recommended

### Recommended Levels

0.5-2.0 % additive (as supplied) based upon the total formulation, depending on the properties of the formulation to be achieved.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

### Incorporation and Processing Instructions

OPTIGEL-WA is hydrophilic and easy to incorporate in water. To ensure optimum distribution and the best possible effectiveness and reproducibility in applications, the additive must be added to water (20 °C ± 5 °C) slowly whilst stirring, and pre-dispersed at high shear forces for at least 20 minutes. OPTIGEL-WA should be fully hydrated before the remaining formulation components can be added to the dispersion. No wetting or dispersing additives are required to produce this dispersion.

OPTIGEL-WA can also be added to the formulation directly, as a powder at the start of manufacture.

# OPTIGEL-WA

Data Sheet  
Issue 10/2016



Additive Guide



**BYK-Chemie GmbH**  
P.O. Box 10 02 45  
46462 Wesel  
Germany  
Tel +49 281 670-0  
Fax +49 281 65735

**info@byk.com**  
**www.byk.com**

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYPK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, PRIEX®, PURE THIX®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® **are registered trademarks of the BYK group.**

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany