

# BYK-220 S

Wetting and dispersing additive for ambient-curing plastic systems and solvent-borne coatings to achieve pigment stabilization and to reduce flooding/floating. Contains silicone.

## Product Data

### Composition

Solution of a low molecular weight, unsaturated acidic polycarboxylic acid polyester with a polysiloxane copolymer

### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Acid value:	100 mg KOH/g
Density (20 °C):	0.96 g/ml
Non-volatile matter (10 min., 150 °C):	52 %
Solvents:	Alkylbenzenes
Flash point:	48 °C

### Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit [www.byk.com](http://www.byk.com) for further information.

### Storage and Transportation

Separation or turbidity may occur during storage and transportation. Mix well before use. Warm to 30-60 °C and mix well.

### Special Note

White spirit-based coating systems or those that are diluted with white spirit have a limited compatibility.

## Applications

### Ambient-curing Plastic Systems

#### Special Features and Benefits

BYK-220 S improves the dispersion of all conventional fillers, such as calcium carbonate and aluminum hydroxide. It reduces the viscosity of the filled resin, which enables an increased filler content. In the majority of cases, the settling of the filler is significantly reduced during storage and when processing. BYK-220 S is suited to stabilizing pigments in gel coats. The additive also contains a small quantity of a polysiloxane copolymer to reduce flooding and floating. This prevents the formation of Bénard cells and improves the surface slip and leveling.

#### Recommended Use

The additive is particularly recommended for unsaturated polyester resins, gel coats, acrylic, polyurethane and epoxy resins and displays the highest efficiency in all applications.

**Recommended Levels**

0.5-1.5 % additive (as supplied) based upon the filler.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

**Incorporation and Processing Instructions**

For optimum performance, the additive should be added before the solids.

**Coatings Industry****Special Features and Benefits**

The additive provides a targeted, controlled flocculation of the pigments. The system builds bridges between the individual pigment particles, thereby creating three-dimensional networks. This controlled flocculation of the pigments primarily prevents flooding/floating along with settling and sagging. BYK-220 S is suited to stabilizing pigments in industrial coatings and architectural coatings. It increases gloss, prevents floating and reduces the millbase viscosity. The additive also contains a small quantity of a polysiloxane copolymer to reduce flooding and floating. This prevents the formation of Bénard cells and improves the surface slip and leveling, and also the orientation of matting agents and aluminum pigments. In the majority of cases, it is no longer necessary to add the silicone additives which are usually required.

**Recommended Levels**

Amount of additive (as supplied) based upon pigment:

Inorganic pigments: 3-10 %

Titanium dioxides: 1-3 %

Organic pigments: 8-16 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

**Incorporation and Processing Instructions**

For optimum performance, the additive must be incorporated into the millbase before addition of pigments.



Additive Guide



**BYK-Chemie GmbH**  
P.O. Box 10 02 45  
46462 Wesel  
Germany  
Tel +49 281 670-0  
Fax +49 281 65735

**info@byk.com**  
**www.byk.com/additives**

ACTAL®, ADJUST®, ADVITROL®, ALUFERSOL®, ANTI-TERRA®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CLAYTONE®, CLOISITE®, COPISIL®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, FULGEL®, FULMONT®, GARAMITE®, GELWHITE®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, NANOBYPK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, SILBYK®, TIXOGEL®, VISCOBYK®, Y-25®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This issue replaces all previous versions – Printed in Germany