



BYK®-L 9505
BYK®-LP A 5551

Air Release Additives for PUR Artificial Leather

Composition

BYK-L 9505	Solution of foam destroying polymers
BYK-LP A 5551	Methylalkyl polysiloxane

Typical Physical Data

	Density at 20°C	Non-volatile matter in %	Flash point in °C
BYK-L 9505	0,95	89,5	68
BYK-LP A 5551	0,91	> 98	> 65

Values indicated in this data sheet describe typical properties and do not constitute specification limits.

Recommended Amounts

	% additive (as supplied) based upon:	
	PUR solution, ready to use	
BYK-L 9505	0,1 – 0,3	
BYK-LP A 5551	0,1 – 0,3	

Application Fields

	PUR Artificial Leather	
	wet process	dry process
BYK-L 9505	●	●
BYK-LP A 5551	●	●
	● recommended	

Special Properties and Advantages

BYK-L 9505	facilitates a rapid deaeration of the PUR solution under vacuum and prevents foaming and air entrapment during the application , silicone free.
BYK-LP A 5551	facilitates a rapid self deaeration of the PUR solution and prevents foaming and air entrapment during the application , contains silicone.

Packaging

Drums and pails

Containers not completely emptied must be closed immediately after use!



Anti-Terra®, BYK®, BYK-Dynwet®, Bykanol®, Byketol®, Bykoplast®, Bykumen®, Disperbyk®, Disperplast®, Lactimon®, BYK®-Silclean®, and Viscobyk® are registered trademarks of BYK-Chemie.

This information is given to the best of our knowledge. Because of the multitude of formulations, production and application conditions, all the above mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

10/03 This data sheet replaces all previous issues - Printed in Germany

BYK-Chemie GmbH, Postfach 100245, 46462 Wesel, Germany
Tel. +49 (0) 281 670-0, Fax +49 (0) 281 65735, info@byk.com, www.byk-chemie.com