

DISPERPLAST-1150

Solvent-free wetting and dispersing additive for PVC- and thermoplastics applications to improve the dispersion and reduce the viscosity of filled and pigmented systems. Suitable for producing liquid color masterbatches and solid masterbatches.

Product Data

Composition

Polar, acidic ester of long chain alcohols

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Acid value:	95 mg KOH/g
Density (20 °C):	1.01 g/ml
Refractive index (20 °C):	1.459
Flash point:	186 °C

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

The product can become solid below 20 °C. Warm to 30-60 °C and mix well. Product is hygroscopic.

Applications

PVC Plastisols

Special Features and Benefits

DISPERPLAST-1150 reduces the viscosity of pigmented and filled PVC plastisols. It is particularly recommended for inorganic pigments, zinc oxide and blowing agents (azodicarbonamide). The product enables a greater solids content, improves the color strength of the pigments and shortens the dispersion time. It also prevents any separation of the plasticizer. The tendency of settling is reduced.

Recommended Levels

Amount of additive (as supplied) based upon solids:

Inorganic pigments:	1-3 %
Organic pigments:	5-7 %
Inorganic fillers:	1-3 %
Blowing agent:	1-2 %
Zinc oxide:	1-3 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive should be added to the liquid components prior to incorporating the solids.

DISPERPLAST-1150 can be used in either a liquid, solid or partially solid form.

The product efficiency is not influenced if it is carefully dispersed in the plasticizer.

Thermoplastics

Special Features and Benefits

DISPERPLAST-1150 absorbs onto the pigment surface and generally enables a better processing and dispersion of the pigments. It is recommended for producing fatty acid-based liquid color masterbatches with inorganic pigments which are used to color thermoplastics (PE, PP, PET). In doing so, it significantly reduces the viscosity therefore enabling a greater pigmentation. The additive is also recommended in solid masterbatches for stabilizing inorganic pigments and effect pigments in PE, PP and PET. In these systems, it improves the torque build-up, the throughput, the viscosity (MVR) and the filter pressure value (FPV).

Recommended Levels

Amount of additive (as supplied) based upon solids:

Inorganic pigments:	0.5-3 %
Titanium dioxides:	0.5-3 %
Effect pigments:	0.5-3 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

For the production of liquid color masterbatches, DISPERPLAST-1150 is slowly added to the carrier system whilst stirring. Only add the pigments once the additive has been uniformly distributed.

For solid masterbatches, it is added to the solids or the polymer carrier before or during compounding.



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com/additives

ACTAL®, ADJUST®, ADVITROL®, ALUFERSOL®, ANTI-TERRA®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CLAYTONE®, CLOISITE®, COPISIL®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, FULGEL®, FULMONT®, GARAMITE®, GELWHITE®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, SILBYK®, TIXOGEL®, VISCOBYK®, Y-25®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This issue replaces all previous versions – Printed in Germany