

SCONA TPPP 8112 GA

Adhesion promoter for TPE-S overmolding compounds and coupling agent for natural fiber compounds in polypropylene.

Product Data

Composition

Polypropylene highly functionalized with maleic anhydride

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

MFR (190 °C, 2.16 kg): > 80 g/10 min

Drying loss (3 h, 110 °C): < 0.5 %

MAH content: 1.4 %

Supplied as: Granulate

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Storage temperature max. 35 °C, relative humidity < 80 %. Avoid direct sunlight and contact with water.

Special Note

The modifier is also available as a powder under the name SCONA TPPP 8112 FA.

Applications

Thermoplastics

Special Features and Benefits

In TPE-S overmolding compounds, the modifier improves adhesion on hard substrates (such as PC, PA, ABS).

Due to the high grafting level, only part of the PP in the TPE compound must be replaced with the modifier.

In PP natural fiber compounds, the product significantly improves the mechanical properties and reduces water absorption.

Recommended Levels

0.8-3 % additive (as supplied) based upon total formulation, depending on the natural fiber content in fiber compounds as well as the PP content in overmolding compounds. The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

Distribute the modifier homogeneously in the compound.



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45

46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This issue replaces all previous versions – Printed in Germany