

SCONA TSPOE 1002 GBLL

Impact strength modifier for polyamide and PET as well as compatibilizer for polyamide blends.

Product Data

Composition

Ethylene octen copolymer functionalized with maleic anhydride

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

MFR (190 °C, 21.6 kg): 6-23 g/10 min
Drying loss (3 h, 110 °C): < 0.5 %
MAH content: 1.45-1.65 %
Supplied as: Translucent granulate

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Storage temperature max. 35 °C, relative humidity < 80 %. Avoid direct sunlight and contact with water.

Applications

Thermoplastics

Special Features and Benefits

SCONA TSPOE 1002 GBLL is a high impact strength modifier for polyamide 6, polyamide 6.6, and polyamide 12 as well as polyethylene terephthalate (PET). In polyamides, it significantly increases low temperature impact strength, and for PET, it improves notch impact strength. In polyamide/PP blends, the product leads to improved impact strength and compatibility. Its low yellowness index makes the product suitable for lighter compounds as well.

Recommended Levels

3-15 % additive (as supplied) based upon total formulation for polyamide.
6-18 % additive (as supplied) based upon total formulation for PET.
2-8 % additive (as supplied) for PA/PP blends in the PP content.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

Incorporate the product with high shear forces by means of a twin-screw extruder. The modifier may be diluted.

SCONA TSPOE 1002 GBL

Data Sheet
Issue 07/2013



Additive Guide



Google play

BYK-Chemie GmbH

P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This issue replaces all previous versions – Printed in Germany