

BYK-TS 3201

Surface additive for polyolefins to improve the scratch resistance of thermoplastic molded parts.

Product Data

Composition

Organically modified siloxane, adsorbed onto a polypropylene carrier

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Bulk density: 280 kg/m³
Melting point (carrier): > 160 °C
Active substance: 66 %

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Storage and transport at room temperature.

Applications

Thermoplastics

Special Features and Benefits

BYK-TS 3201 increases the scratch resistance of surfaces of thermoplastic molded parts based on polyolefins e.g. polypropylene (PP). In addition it is used to enhance the surface slip of thermoplastic materials. Dosages from 1-3 % result in a significant improvement of the scratch resistance of thermoplastic surfaces when used in vehicle interiors for example.

Recommended Levels

1-3 % additive (as supplied) based upon the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive is added at the same time as the other raw materials; it is also possible to incorporate the additive later. A concentration test series will be helpful to adjust the right dosage for each formulation.



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45

46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This issue replaces all previous versions – Printed in Germany