

# ®Vinnolit S 3368

Suspension-PVC for thermoplastic processing of PVC

## **Brief Description**

<sup>®</sup>Vinnolit S 3368 is a porous suspension polymer with high bulk density. It is recommended for rigid profile, sheet and pipe extrusion.

Raw Material Properties	Typical Value*	Unit	Test Method	
			DIN EN ISO	ISO
K-Value	68	-	1628-2	1628-2
Reduced viscosity	116	ml/g	1628-2	1628-2
Apparent bulk density	0.580	g/ml	60	60
Particle size distribution: Sieve retention R retained on 0.063 mm screen retained on 0.250 mm screen	≥ 95 ≤ 5	% %	4610 4610	4610 4610
Volatile matter	≤ 0.3	%	1269	1269

<sup>\*</sup> The values given above are **typical** test results which should be used as a guide only. They do not form the whole or part of a specification or guarantee.

#### **Product Information**

#### **Processing and Applications**

Vinnolit S 3368 can be converted into themoplastic processible compounds with the usual additives by standard mixing techniques.

Mixtures containing Vinnolit S 3368 fuse rapidly and can be extruded at high output rates.

Principal application areas are:

- rigid profiles
- sheets
- pipes

### Packaging, Delivery and Storage

The product is supplied in 25 kg bags as well as in bulk form.

Vinnolit S 3368 should be stored dry and away from direct or indirect sources of heat. Please consult the safety data sheet for information about the safety precautions necessary for transport, storage, blending and processing.

#### **General Information**

Further processing information and recommendations can be obtained from our Technical Service or our local representatives.

The data and recommendations contained in this product information represent the current state of our knowledge and serve as a guide only to our products and their potential applications. Therefore, no warranty of specific properties of the products mentioned herein nor of their suitability or fitness for a particular purpose is implied.

The information given in this leaflet should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also used. Patent or other proprietary rights of third parties must be observed. The quality of our products is warranted under the terms of our General Conditions of Sale.

Ismaning, November 2014

Vinnolit GmbH & Co. KG

Carl-Zeiss-Ring 25 85737 Ismaning Germany

Tel.: +49 89 9 61 03-0 Fax: +49 89 9 61 03-103

www.vinnolit.com A Westlake Company